

## **MA6340B**

# **Technical Data Sheet**

#### A. Identification

Product description:

High molecular weight silicone di-acrylate based surface additive

and pre-polymer

Used as an additive for UV or E-beam curable printing inks, coatings and adhesives with permanent slip and remarkable tape

release property

Used as a pre-polymer to be co-reacted into acrylic polymers for coatings, plastic, resin and other applications to improve the surface and physical properties like release characteristics, mar

resistance, flexibility and hydrophobicity.

• Product code: MA6340B

#### **B.** Product Data

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Appearance: Colorless to Light yellow clear liquid

• Active constituent: 100%

• Specific gravity (25  $^{\circ}$ C): 0.98

• Viscosity (25 °C, cps): 80-180

• Molecular weight (Mw): 11,000-14,000

• Functional group: 2

• Refractive index: 1.408

### C. Product Highlights

- Non-migratory property via its acrylic functionality.
- Remarkable surface smoothness, anti-blocking and mar resistance properties.
- Tape release characteristics.



#### D. Recommended Use & Levels

- 0.1-1.5% as an additive (as supplied) based upon total formulation for UV curing systems.
- 2.0-10.0% as a pre-polymer for release liner coatings, plastic coatings and other applications.

## E. Packing

• 10Kg pails, 180Kg plastic lined steel drums or other specified package.

### F. Storage & Handling

- The recommended storage temperature is between 4  $^{\circ}$ C to 40  $^{\circ}$ C.
- Product should be stored in a cool, dry place, away from direct sunlight.
- The containers should be kept sealed and away from oxidizing agents, acids, alkalis.